



## Premium Finish



The finishing process was especially developed to meet the highest requirements in terms of precision.

### Facts

- Increase of parallelism to 0,02 mm related to a thickness tolerance of +/- 0,02 mm
- Applicable to all compression-proofed Brandenburger high-performance insulation materials max. raw dimension 1.500 mm x 1.250 mm (length x width)

### Advantages

- Highest fitting accuracy of high-performance insulation boards
- Increased dimension precision in the overall structure
- Optimized quality in the production of precision components



© Zahoransky Formenbau GmbH





Consulting + Service



Production + Machining



Finishing



Research + Development

## Brandenburger thermal insulation materials suitable for Premium Finish

	Temperature resistance in °C		Compressive strength at		Coefficient of thermal conductivity in W/mK DIN 52 612
	long-therm	short-therm	23 °C in N/mm <sup>2</sup> EN ISO 604	200 °C in N/mm <sup>2</sup> EN ISO 604	
KV <sup>®</sup> 3	250	280	650	450	0,25
KV <sup>®</sup> 3eco	250	280	650	500	0,25
BRA-GLA <sup>®</sup> SI	280	350	450	200	0,22
BRA-GLA <sup>®</sup> 3	230	250	650	350	0,30
BRA-GLA <sup>®</sup> N	210	230	600	290	0,30
S 4000 <sup>®</sup> HT	230	250	450	200	0,13
S 4000 <sup>®</sup>	210	250	300	100	0,12
XGD <sup>®</sup> 60	210	250	610	300	0,30
XGD <sup>®</sup> 25	200	230	350	150	0,12
XGD <sup>®</sup> 16	180	200	340	130	0,18
GL <sup>®</sup> P	500	800	330	240	0,31
GL <sup>®</sup> M	400	600	400	250	0,30

*“simply better insulated”*

 Brandenburger



Brandenburger Isoliertechnik GmbH & Co. KG  
 Taubensuhlstr. 6  
 D - 76829 Landau  
 Tel: +49 6341 / 5104-0  
 Fax: +49 6341 / 5104-155  
 info@brandenburger.de